

Reverberatory Furnace – Subhearth

Aluminum Alloy

Products	Chemistry (%)		Density		Temperature Limit	
	Al ₂ O ₃	SiO ₂	g/cm ³	lb/ft ³	°C	°F
BETAMAX® 24 LT	41.3	38.9	1.30	81	1315	2400
MATRICAST 2600 AC	42.7	43.3	2.03	127	1425	2600
MATRIPUMP 45 AL	47.0	46.9	2.35	147	1370	2500
NANO-TEK® 45 AL	44.6	50.4	2.08	130	1425	2600